

TG-800

K值 K-Value	62
聚合度 Degree of Polymerization	760-860
表观密度 Bulk Density (g/cc)	0.58
颗粒尺寸 (42目网筛网通过率 [%]) Particle Size (42 Mesh Pass [%])	≥ 99.50
挥发量 (%) Volatile Matters (%)	≤ 0.50
外观 Appearance	白色粉末 White Powder

Test Method K-Value: JIS K7367-2
Bulk Density: JIS K7365
Volatile Matter: JIS K7382

适用范围 Applications

硬质板材 Rigid Plates
压延片材 Various Extruded Sheet
压延薄膜 Draw Films
吹瓶 Bottles
透明软片 (压延)
Transparent Soft Sheets (Calendering)
注射成型模具制品 (接头等)
Injection Molded Products (Fittings, etc)
排水槽 Weather Strips

优越性能 Special Features

干流性好
Excellent Dry Flow Characteristics
与增塑剂和液体稳定剂的混合性好
Excellent Miscibility with Plasticizer and Liquid Stabilizer
超高速吸收增塑剂
Extremely Fast Rate of Plasticizer Absorption
热稳定性高
High Thermal Stability
批间质量稳定
Lot-to-Lot Uniformity

