

TG-700

K值 K-Value	59
聚合度 Degree of Polymerization	670-770
表观密度 Bulk Density (g/cc)	0.58
颗粒尺寸 (42目筛网通过率 [%]) Particle Size (42 Mesh Pass [%])	≥ 99.50
挥发量 (%) Volatile Matters (%)	≤ 0.50
外观 Appearance	白色粉末 White Powder

Test Method K-Value: JIS K7367-2
Bulk Density: JIS K7365
Volatile Matter: JIS K7382

适用范围 Applications

硬质板材 Rigid Plates
压延片材 Various Extruded Sheets
压延薄膜 Draw Films
吹瓶 Blow Bottles
硬片/软片 (压延) Rigid/Flexible Sheets (Calendering)
注射成型模具制品 (接头、电器插座等)
Injection Molded Products (Fittings, Electrical Plugs)

优越性能 Special Features

干流性好 Excellent Dry Flow Characteristics
热稳定性高 High Thermal Stability
批间质量稳定 Lot-to-Lot Uniformity

