



TG-1000R

K 值 K-Value	65.3-68.1
聚合度 Degree of Polymerization	960-1100
表观密度 Bulk Density (g/cc)	0.51-0.61
颗粒尺寸 (42 目筛网通过率[%]) Particle Size (42 mesh Pass [%])	≥99.5
挥发量 (%) Volatile Matter	≤0.50
外观 Appearance	白色粉末 White Powder

Test Method K-Value: JIS K7367-2
 Bulk Density: JIS K7365
 Volatile Matter: JIS K7382

适用范围 Applications

管材 Pipes
波纹屋顶 Corrugated Roofing Sheets
套管 Conduits
型材 (门框、窗框等) Profiles (Doors, Windows, etc.)
弹性地砖 Floor Tiles

优越性能 Special Features

干流性好 Excellent Dry Flow Characteristics
热稳定性高 High Thermal Stability
批间质量稳定 Lot-to-Lot Uniformity